

# tesa® 4952

Double-sided PE-foam mounting tape

## PRODUCT INFORMATION

### Product Description

tesa® 4952 is a double-sided PE-foam tape for constructive mounting applications. It consists of a highly conformable PE-foam backing and a tackified acrylic adhesive. tesa® 4952 has been externally certified for furniture mirror mounting.

Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- Fully outdoor suitable: UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorption

### Main Application

- Furniture mirror mounting
- Mounting of car mirrors
- Mounting functional trims & profiles
- Mounting of decorative panels

### Technical Data

■ Backing material	PE foam	■ Tensile strength	10 N/cm
■ Colour	white	■ Type of liner	glassine
■ Total thickness	1150 µm	■ Thickness of liner	70 µm
■ Type of adhesive	tackified acrylic	■ Colour of liner	brown
■ Elongation at break	200 %	■ Weight of liner	80 g/m <sup>2</sup>

### Adhesion to

■ Steel (initial)	6.5 N/cm	■ Steel (after 14 days)	8.0 N/cm
■ ABS (initial)	5.0 N/cm	■ ABS (after 14 days)	8.0 N/cm
■ Aluminium (initial)	5.0 N/cm	■ Aluminium (after 14 days)	8.0 N/cm
■ PC (initial)	5.0 N/cm	■ PC (after 14 days)	8.0 N/cm
■ PE (initial)	2.7 N/cm	■ PE (after 14 days)	2.8 N/cm
■ PET (initial)	5.0 N/cm	■ PET (after 14 days)	7.0 N/cm
■ PP (initial)	2.8 N/cm	■ PP (after 14 days)	5.5 N/cm
■ PS (initial)	5.0 N/cm	■ PS (after 14 days)	7.5 N/cm
■ PVC (initial)	5.0 N/cm	■ PVC (after 14 days)	8.0 N/cm

For latest information on this product please visit <http://l.tesa.com/?ip=04952>

Page 1 of 2 / As of 06/16/13

## tesa® 4952

Double-sided PE-foam mounting tape

### PRODUCT INFORMATION

#### Properties

■ Temperature resistance short term	80 °C	■ Resistance to chemicals	+
■ Temperature resistance long term	80 °C	■ Softener resistance	o
■ Tack	+	■ Static shear resistance at 23°C	+
■ Ageing resistance (UV)	+	■ Static shear resistance at 40°C	+
■ Humidity resistance	++		

Evaluation across relevant tesa® assortment: ++ very good, + good, o medium, - low

#### Additional Info

tesa® 4952 has been tested and approved by LGA institute for mirror mounting. Report number IWQ FSG 329 1189.

Peel Adhesion:

- immediately: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

For latest information on this product please visit <http://l.tesa.com/?ip=04952>

Page 2 of 2 / As of 06/16/13

#### tesa SE

Quickbornstraße 24  
20253 Hamburg  
Germany  
Phone: +49 (40) 4909 101  
<http://www.tesa.com>

#### tesa tape inc.

5825 Carnegie Boulevard  
Charlotte, N.C. 28209  
United States of America  
Phone: +1 (704) 554 0707  
Fax: +1 (704) 553 5634  
<http://www.tesatape.com>

#### tesa tape Asia Pacific Pte. Ltd.

164 Gul Circle,  
Singapore 629621  
Phone: +65 (68) 612 026  
Fax: +65 (68) 614 790  
<http://www.tesa-asia.com>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to advise you.